



1501 West 178th Street | Gardena, CA. 90248
310-767-7812 | 800-359-5679 | fax: 310-767-7836
info@matsui-color.com | www.matsui-color.com

WB0312 RC Spot Black

Technical Data Sheet

- **Wet Ink Tack** | Low
- **After Flash Tack** | Low
- **Printability** | Excellent
- **Surface Appearance** | Matte
- **Opacity/Viscosity** | High/Low
- **Bleed Resistance** | None
- **Flash Temperature** | 160°F (71°C)/decreases with deposit thickness
- **Cure Temperature** | 320°F (160°C)
- **Squeegee Hardness** | Medium
- **Squeegee Blade** | Sharp
- **Squeegee Angle** | 45 degrees to screen
- **Squeegee Speed** | Medium
- **Underlay** | N/A
- **Emulsion** | Direct or indirect
- **Mesh Count** | 110-305 mc in (43-120 mc cm)
- **Thinner** | RV Additive
- **Thickener** | Thickener B
- **Storage** | 65°F to 95°F (18°C to 35°C). Avoid direct sun.
- **Cleanup** | Water and mild soap or detergent
- **Color Range** | Black
- **Substrate Type** | All
- **Substrate Color(s)** | Light, Medium and Dark Fabrics

Description

RC Spot Black is a Premium high mesh direct printing black for halftone or spot printing to achieve an extremely soft hand feel. This product has a black matte appearance.

Features

- Easy to print
- Exceptional halftone and spot black
- Prints through very high mesh counts for minimum ink usage
- Excellent printability with no viscosity modifications
- Extremely soft hand feel that PVC inks cannot achieve
- OEKO-TEX® Compliant, CPSIA and HR4040 Compliant
- Is “PVC Free” and environmentally safe

Application

Print through fine screen mesh up to 305 mc in (120 mc cm) when cured at 320°F (160°C), **RC Spot Black** produces the softest prints achievable in textile screen printing today.

Special Recommendations

RC Spot Black should be mixed in clean vessels using clean mixing blades and utensils. Any contamination from other ink sources or non-approved additives could make **RC Spot Black** test positive for restricted PVC's.

- **RC Spot Black** can be dry cleaned or ironed
- Use Retarder MG 1-5% to help with open time in the screen
- Use Fixer WF-N 1-5% to help with wash fastness
- Use Softener MG 1-4% to help penetrate in to the garment
- Use Thickener B .25-1% to help thicken the ink
- Use RV Additive 1-3% to reduce viscosity