



1501 West 178th Street | Gardena, CA. 90248
310-767-7812 | 800-359-5679 | fax: 310-767-7836
info@matsui-color.com | www.matsui-color.com

WS0525 Soft Stretch White

Technical Data Sheet

- **Wet Ink Tack** | Low
- **After Flash Tack** | Low
- **Printability** | Excellent
- **Surface Appearance** | White
- **Opacity/Viscosity** | High/Med
- **Bleed Resistance** | None
- **Flash Temperature** | 160°F (71°C)/decreases with deposit thickness
- **Cure Temperature** | 320°F (160°C)
- **Squeegee Hardness** | Medium
- **Squeegee Blade** | Sharp
- **Squeegee Angle** | 45 degrees to screen
- **Squeegee Speed** | Medium
- **Emulsion** | Direct or indirect
- **Mesh Count** | 150-180/inch (59-70/cm)
- **Thinner** | RV Additive
- **Thickener** | Thickener B
- **Storage** | 65°F to 95°F (18°C to 35°C). Avoid direct sun.
- **Cleanup** | Water and mild soap or detergent
- **Color Range** | White
- **Substrate Type** | Cotton, Polyester
- **Substrate Color(s)** | Light, Medium Dark Fabrics

Description

Soft Stretch White is a White mixing base for “**Performance**” and high stretch fabrics that can be mixed with “**Neo Pigments**” to achieve “Silicone like” finish which hand feel is extremely soft and has excellent elasticity.

Features

- Easy to mix and print
- Creates thousands of color shades by adding up to 15% Neo Pigments
- Excellent printability with no viscosity modifications
- Extremely soft hand feel that PVC inks cannot achieve
- Excellent elasticity, great on Dri-fit performance fabrics
- Creates tone on tone look with superb softness
- Is “**PVC Free**” and environmentally safe

Application

Print through fine screen mesh (150 ~ 180/inch recommended) when cured at 320°F (160°C), **Soft Stretch White** produces the soft and “Silicone like” prints.

For print on dark colored polyester, print Under Base Blocker first, flash and then print this Soft Stretch White onto it.

Special Recommendations

Soft Stretch White should be mixed in clean vessels using clean mixing blades and utensils. Any contamination from other ink sources or non-approved additives could make **Soft Stretch White** test positive for restricted PVC's.

- **Print of Soft Stretch White can be ironed**
- **Use Retarder MG 1-5% to help with open time in the screen**
- **Use Fixer WF-N 1-5% to help with wash fastness**
- **Use Thickener B .25-1% to help thicken the ink**
- **Use RV Additive 1-3% to reduce its viscosity**